



RAINBOW

SOLVENTFREE AMINE-CURED EPOXY FOR WATER TANK MIL-PRF-23236D TYPE V CLASS 9 GRADE C



Specification Data

Product Number	EP-4567
Type	The two-pack solventless water tank coating based on Bisphenol A epoxy resin and polyamine resin with anticorrosive pigment.
Uses	Used for new water tank or maintenance old one to prevent rust, also suitable for steel and concrete structure, such as chemical plant, bridge, power plants, inlet and outlet water pipe, water ditch, sewer etc.
Characteristics	<ol style="list-style-type: none"> 1. Good adhesion with steel or concrete substrate. 2. Excellent resistance to water and corrosion. 3. Good compatible with cathode protection system. 4. No VOC emissions in the coating. 5. The paint for white color obtains NSF ANSI 61 certificate, suitable for potable water tank lining. 6. Compliant with U.S. Navy military specification MIL-PRF-23236D TYPE V CLASS 9 GRADE C 7. https://qpldocs.dla.mil/ (Search MIL-PRF-23236D TYPE V CLASS 9 GRADE C)
Color	White
Finish	Gloss
Density	Above 1.4Kg/L (mixture)
Viscosity	Approx. 110KU (mixture, 25°C)
Primer	NO.1073 (On Concrete)
Overcoating Intervals	Min. 12hrs Max. 10days (25°C)
VOC Values	Solvent-free
Volume Solids	100%(mixture)
Theoretical Coverage	19.2 m ² /Gal(DFT150 μm)
Pot Life	Above 1hr (mixture 25°C)
Dry Film Thickness	150 μm (Wet : 150 μm)
Repair	Self Repairing

Performance Data

Test Method	System	Results
NSF/ANSI 61 Drinking Water System Components-Health Effects	1 ct. EP.4567 (150 microns) 1 ct. EP.4567 (150 microns)	Pass
MIL-PRF-23236D TYPE V CLASS 9 GRADE C	1 ct. EP.4567 (150 microns) 1 ct. EP.4567 (150 microns)	QUALIFIED

Test reports and additional data available upon written request.

EPDM10EP4567 V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443



RAINBOW

Certification

- NSF/ANSI 61 Drinking Water System Components-Health Effects
- MIL-PRF-23236D TYPE V CLASS 9 GRADE C

Application Instruction

• Surface preparation

General

Remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Surfaces must be clean and dry. Moisture, grease, sludge, dust, corrosive salt must be thoroughly cleaned from substrate.

Steel

Surface preparation standards can use SSPC-SP10 or Sa2 1/2 (ISO 8501-1:2007).

Primed Surfaces

NO.4567 should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination and NO.4567 must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of Breakdown and Damage

It should be prepared to the specified standard (Sa2 1/2 (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of NO.4567.

• Mixing & Thinning

Mixing

Mix base and hardener according to the mixing ratio and stir thoroughly.

Thinning

Use Epoxy Thinner (SP-12) to thin up 5-10%.

Mixing Ratio

Base : Hardener = 3 : 1 (by volume)

Pot life

Above 1 hour at 25°C (mixture, 77°F)

• Equipment

Spray

Application

Avoid applying the paint in rainy weather or the relative humidity exceed 85%, particularly, a wet surface must be thoroughly dried. All equipment must be cleaned immediately after use. To increase or decrease the usage of thinner depending on the temperature of the coated surface, the temperature decreased may have to add more amount of thinner

Airless

Spray

Pump ratio 60:1 or greater

Tip size : 0.019"~ 0.025"

Input PSI: 85 Output PSI : 2800~4000.

Brush

Application by brush is applicable. For special condition please consult with product manufacturer.

Roller

Application by roller is applicable. For special condition please consult with product manufacturer.

EPDM10EP4567 V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443



RAINBOW

- Environment conditions

Condition	Coating	Surface	Environment	Humidity
Minimum	10°C (50°F)	10°C (50°F)	10°C (50°F)	30%
Maximum	35°C (95°F)	55°C (131°F)	45°C (113°F)	85%

Industry standards are for substrate temperatures to be 3°C (5°F) above the dew point . the product simply requires the substrate temperature to be above the dew point.

- Curing Schedule

Surface Temp. & 50% Relative Humidity	Set to touch	Dry Hard	Fully Cured
10°C (50°F)	12 hours	24 hours	14 days
15°C (59°F)	8 hours	16 hours	10 days
25°C (77°F)	4 hours	8 hours	5 days
35°C (95°F)	3 hours	6 hours	4 days

- Cleanup & Safety

Cleanup

Use Epoxy Thinner (SP-12) to clean. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety

Please read and follow all caution statements on this product data sheet and SDS for this product.

Ventilation

Proper ventilation and protective measures must be provided during application and drying to keep solvent vapor concentrations within safe limits and to protect against toxic or oxygen deficient hazards.

- Package, Handling & Storage

Shelf Life

Part A :Minimum 1 years under normal storage conditions
Part B :Minimum 1 years under normal storage conditions

Shipping Weight

Part A : 1 Gallon – 3.9kg 5 Gallon – 19.5kg
Part B : 1 Gallon – 1.3kg 5 Gallon – 6.5kg

Storage Temperature & Humidity
Flash Point
Storage

5-35°C (41-95°F)
0-90% Relative Humidity

Above 100°C(mixture)
Store in cool ventilated place, do not exposed to the sun in outdoor to avoid affecting the quality.

EPDM10EP4567 V1.0

YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181
FAX:886-7-8715443