



RAINBOW

EPOXY ELASTOMER PUTTY

NO.	No. 1080 EP
TYPE	A two-pack special compound based Elastomer Resin, Hardener, and chemical resistance pigments.
USES	Surfacer for steel decks and floors.
CHARACTERISTICS	<ol style="list-style-type: none">1. Excellent resistance to oil, water and chemical.2. Excellent adhesion to steel and concrete.3. Outstanding abrasion, elastically flexible and load resistant. No cracking under heavy load.4. Anti-corrosive well.
APPLICATION METHOD	Manual trowling
DRYING TIME (25 °C)	Set-to-touch 6 hrs. Dry hard 24 hrs. Fully cured 7 days.
OVERCOATING INTERVALS (25 °C)	Min. 24 hrs. Max. 2 days.
THINNER	SP-12 Epoxy Thinner (only for cleaning tools)
STORAGE SHELF LIFE	Minimum 1 year under normal storage
POT LIFE (25 °C)	1 hrs. (Mixture)
NOTE	<ol style="list-style-type: none">1. Mix base, hardener according to the mixing ratio and thoroughly.2. Avoid applying the paint in rainy weather or humidity above 85% RH, particularly, a wet surface must be thoroughly dried.3. All equipments must be cleaned immediately after use.

YUNG CHI PAINT & VARNISH MFG. CO., LTD

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181 FAX : 886-7-8715443