



# RAINBOW

## SUPERMARINE

PRODUCT NUMBER	SP-60 ( OF-53 ) / SP-61 ( OF-51 ) / SP-65 ( OF-56 ) / SP-74		
TYPE	A finish paint based on long oil alkyd resin with weather resistant pigment.		
USES	Topcoat for superstructures, steel structures, deck fittings, interior rooms and woodworks.		
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Good appearance and gloss retention..</li><li>2. Good abrasion and weather resistance.</li><li>3. Good adhesion to oleoresinous and chlorinated rubber primers.</li><li>4. Capable of with-standing temperature up to 80°C (176°F).</li><li>5. Good resistance to oil and water.</li><li>6. Easy application.</li></ol>		
FINISH	Gloss		
COLOR	SP-60 ( OF-53 ) : # 30 / SP-61 ( OF-51 ) : White SP-65 ( OF-56 ) : Desired colors / SP-74 : Desired colors		
FLASH POINT	Above 25°C (77°F)		
SPECIFIC GRAVITY	Above 1.1 Kg/L		
VISCOSITY	70 ~ 90 KU (25°C)		
DRYING TIME	Set-to-touch 3 hrs.	Dry hard	15 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 70 microns (2.8 mil)	Dry	35 microns (1.4 mil)
THEORETICAL COVERAGE	54.9 m <sup>2</sup> /Gal	14.5 m <sup>2</sup> /L	13.2 m <sup>2</sup> /Kg
OVERCOATING INTERVALS	Min. 24 hrs. (25°C)		
VOLUME SOLIDS	Above 50 %		
THINNER	No.805 Paint Thinner ( OM-07 )		
THINNING RATE	5~10 % (cleaning tools excluded)		
PRECEDING COATS	SP-54 High Red Lead Primer ( OP-91 ) SP-55 Zinc Chromate Primer ( OP-93 ) SP-56 Red Oxide Primer ( OP-95 ) No.920 LZI Primer ( OP-94 )		
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.		
APPLICATION METHOD	Airless Spray, Brush, Roller		
FOR AIRLESS SPRAY	Tip Size	Graco 621, 721	
	Air Pressure	3~5 Kg/cm <sup>2</sup>	
	Pump Ratio	45 : 1 or 33 : 1	

EPDM72OF56XX V1.2

# YUNG CHI PAINT & VARNISH MFG. CO., LTD.

No.26, Yen Hai 3rd Road, Kaohsiung, Taiwan.  
<http://www.rainbowpaint.com.tw>

TEL:886-7-8713181  
FAX:886-7-8715443