

CONTIZINC 2701 (IZ-01)

INORGANIC ZINC RICH PRIMER

TYPE

A two-packs, solvent based inorganic zinc rich rust preventive coating is based on ethyl silicate and high purity zinc dust.

USES

Use for steel structures of power plants, harbor facilities, bridges, water pipelines and storage tanks to extend the protection of life.

CHARACTERISTICS

- High zinc loading.
- Excellent resistance to oil, mechanical damage and organic solvents.
- High slip co-efficient, can be used on faying surface.
- High performance anti-corrosion coating.
- Available in ASTM D520, Type II (low lead) zinc dust version as standard.
- Containing 79% zinc by weight in the dry film. Conforms to SSPC Paint 20 Level 2.

PRACTICAL INFORMATION

Color	Gray
Gloss Level	Flat
VOC Values	4 lbs/gal (480 g/l)
Volume Solids	Above 60%
Theoretical Coverage	3 mils : 326 ft ² /gal (8 m ² /l) 4 mils : 244 ft ² /gal (6 m ² /l)
Typical Thickness	DFT : 2~3 mils WFT : 3.3~5 mils
Service Temperature	Untopcoated: Continuous 750°F (400°C); Non-Continuous 800°F (427°C). With recommended Inorganic copolymer topcoat (CONTITHERM 2569 Min.DFT 2mils) Continuous 1000°F (538°C); Non-Continuous 1200°F (649°C)
Preceding Coats	Chlorinated Rubber, Epoxy, Vinyl, Silicone or PU system A mist coat is required to minimize topcoat bubbling except for some topcoats (high-solids epoxy)
Repair	CONTIZINC 1727

SUBSTRATES & SURFACE PREPARATION

General	Remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Surfaces must be clean and dry. Moisture, grease, sludge, dust corrosive salt must be thoroughly cleaned from substrate.
----------------	---

CONTIZINC 2701 (IZ-01)

INORGANIC ZINC RICH PRIMER

SUBSTRATES & SURFACE PREPARATION

Steel	Surface preparation standards can be used SSPC-SP10 · Sa2 1/2 (ISO 8501-1:2007) or hand rusting to SIS St3. Roughness for structure of carbon steel requires for 45~60 microns.
Stainless & Galvanized	Not recommended application.
Areas of Breakdown and Damage	Should be prepared to the specified standard (Sa2 1/2 (ISO 8501-1:2007) or SSPC-SP6, Abrasive Blasting or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of CONTIZINC 1727(EP-03AA).

PERFORMANCE DATA

Test Method	System	Results
CNS 11584 K6854 Test for Inorganic Zinc Rich Primer	1 ct. IZ-01	Solids content : 80.65% Zinc content in dry film : 86.7%
ISO 4628-6-07 ASTM D610-08 Cyclic Corrosive Test	Blasted Steel 1 ct. IZ-01 (75 microns) 1 ct. 1569 (50 microns)	Chalking rating : 0.5 Rust grade : 10
ISO 4628-6-07 ISO 4624-02 Cyclic Corrosive Test	Blasted Steel 1 ct. IZ-01 (75 microns) 1 ct. EP-999GF (150 microns) 1 ct. UP-450 (60 microns)	Chalking rating : 0.5 Original adhesive strength : 5.2 MPa Percentage of adhesive strength retention after cyclic corrosive test : 62.9%(3.27 MPa)
ASTM D5894-96 ASTM D4541-09 Type V Cyclic Corrosive Test	Blasted Steel 1 ct. IZ-01 (75 microns) 1 ct. EP-999GF (150 microns) 1 ct. UP-450 (60 microns)	No cracking and peeling in appearance Original adhesive strength : 8.0 MPa Percentage of adhesive strength retention after cyclic corrosive test : 69.6%(5.57 MPa)
CNS 11478 K6820 (1995) Test For Heat Resistance Paint (600°C, 48 hours)	Blasted Steel 1 ct. IZ-01 (75 microns) 1 ct. 1569 (50 microns)	No blistering, cracking and peeling in appearance
ASTM B117 Salt Spray	Blasted Steel 1 ct. IZ-01 (75 microns)	No blistering, cracking and rusting after 5000 hrs

CONTIZINC 2701 (IZ-01)

INORGANIC ZINC RICH PRIMER

PERFORMANCE DATA

Test Method	System	Results
ASTM A325 Slip Co-efficient	Blasted Steel 1 ct. IZ-01 (125 microns)	0.47
ASTM F963 Soluble Heavy Metals Test	1 ct. IZ-01	n.d. (Sb 、 As 、 Cd 、 Cr 、 Pb 、 Hg 、 Ba 、 Se)

Test reports and additional data available upon written request.

CERTIFICATION

- CNS 4397 K2088 : Report number 90A0047 (National Kaohsiung University of Applied Sciences)
- Norsok M-501-04 : Report number KV-13-04545XA-1, KV-12-08801XA-1 (SGS Taiwan Ltd.)
- CNS 2949 K2050 : Report number KV-14-10793ZA (SGS Taiwan Ltd.)

MIXING & THINNING

Mixing	Mix base and zinc dust according to the mixing ratio and stir thoroughly.
Thinning	Use CONTITHINNER 13(SP-13) to thin up 5-10%
Mixing Ratio	Base : Zinc dust = 75 : 25 (by volume)
Pot Life	4 hours at 77 °F (mixture, 25°C)

APPLICATION EQUIPMENT GUIDELINES

Spray Application	<p>When the relative humidity is lower than 40%, water should be sprayed on after being painted for 30 minutes to promote hardening. The dry film thickness should not exceed 5 mils to avoid cracking. CONTIZINC 2701 does not suitable for repairing or recoating.</p> <p>Please use product CONTIZINC 1727(EP-03AA) for repairing to avoid layer film cracking.</p> <p>When overcoating, the air in the pores will escape through the next coating and may cause blister. A mist coat then full coat can reduce this condition: spray a thin coat to fill the pores in the CONTIZINC 2702(IZ-01) film, soon after apply to full specified film thickness to break the blisters.</p> <p>Caution : In difficult cases it may be necessary to thin the next coat.</p>
Airless Spray	<p>Pump ratio : 30:1 or greater</p> <p>Tip size : 0.015”~0.021”</p> <p>Output PSI : 2500~3800 PSI</p>

CONTIZINC 2701 (IZ-01)

INORGANIC ZINC RICH PRIMER

APPLICATION EQUIPMENT GUIDELINES

Brush	For touch-up of areas less than one square foot only. Use medium bristle brush and avoid re-brushing.
Roller	Not recommended

APPLICATION CONDITIONS

Condition	Coating	Surface	Environment	Humidity
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	40%
Maximum	113°F (45°C)	122°F (50°C)	113°F (45°C)	—

CURING SCHEDULE

Surface Temp. (50% Relative Humidity)	Touch Dry	Hard Dry	Dry to Handle
59°F (15°C)	45 minutes	1 day	7 days
77°F (25°C)	45 minutes	18 hours	5 days
122°F (50°C)	15 minutes	8 hours	3 days

OVERCOATING INTERVAL

Surface Temp. (50% Relative Humidity)	Minimum	Maximum
59°F (15°C)	8 days	5 days
77°F (25°C)	4 hours	3 days
122°F (50°C)	2 hours	3 days

CLEANER & SAFETY

Cleaner	Use CONTITHINNER 13(SP-13) to clean. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety Ventilation	Please read and follow all caution statements on this product data sheet and MSDS for this product. Proper ventilation and protective measures must be provided during application and drying to keep solvent vapor concentrations within safe limits and to protect against toxic or oxygen deficient hazards.

PACKAGE, HANDLING & STORAGE

Shelf Life	Minimum 12 months under normal conditions.	
Shipping Weight	1 Gallon Kit – Part A : 3.5 kg Part B : 6.5 kg	3 Gallon Kit – Part A : 10.5 kg Part B : 19.5 kg
Storage Temperature & Humidity	5-35°C (41-95°F) 0-90% Relative Humidity	

CONTIZINC 2701 (IZ-01) INORGANIC ZINC RICH PRIMER

**PACKAGE,
HANDLING &
STORAGE****Flash Point**

Part A : 77°F (25°C)

Part B : 77°F (25°C)

Storage

Base and zinc powder storage cannot sunlight exposure or temperature exceeds 104°F (40°C)