



# RAINBOW

## DECK PAINT

PRODUCT NUMBER	SP-59 (OD-41) / SP-62 (OD-44)
TYPE	Deck paint based on alkyd and special resins with weather resistant pigment.
USES	Topcoat for steel decks.
CHARACTERISTICS	<ol style="list-style-type: none"><li>1. Tough and tight film.</li><li>2. Good resistance to abrasion and weather..</li><li>3. Good resistance to oil and water.</li><li>4. Good adhesion.</li><li>5. Easy application.</li></ol>
FINISH	Gloss
COLOR	SP-59 : Red oxide / SP-62 : Green / Black or Gray
FLASH POINT	Above 30°C (86°F)
SPECIFIC GRAVITY	Above 1.2 Kg/L
VISCOSITY	70 ~ 85 KU (25°C)
DRYING TIME	Set-to-touch 1 hr.                      Dry hard 8 hrs. (25°C)
OPTIMUM FILM THICKNESS	Wet 80 microns (3.2 mil)              Dry 35 microns (1.4 mil)
THEORETICAL COVERAGE	47.3 m <sup>2</sup> /Gal              12.5 m <sup>2</sup> /L              11.4 m <sup>2</sup> /Kg
OVERCOATING INTERVALS	Min. 8 hrs. (25°C)
VOLUME SOLIDS	Above 44 %
THINNER	No.805 Paint Thinner (OM-07)
THINNING RATE	5~10 % (cleaning tools excluded)
PRECEDING COATS	SP-54 High Red Lead Primer (OP-91) SP-55 Zinc Chromate Primer (OP-93) SP-56 Red Oxide Primer (OP-95)
STORAGE SHELF LIFE	Minimum 1 year under normal storage conditions.
APPLICATION METHOD	Airless Spray, Brush, Roller
FOR AIRLESS SPRAY	Tip Size              Graco 621, 721 Air Pressure        3~5 Kg/cm <sup>2</sup> Pump Ratio        45 : 1    or    33 : 1

**YUNG CHI PAINT & VARNISH MFG.CO.,LTD**

26. YEN HAI 3RD ROAD. KAOHSIUNG, TAIWAN

TEL : 886-7-8713181    FAX : 886-7-8715443